ADBRI Cement
ABN 96 007 870 199

Cement Test Certificate

Final

845 Stockwell Road, Angaston SA 5353
PO Box 229, Angaston SA 5353
T: +61 8 8561 3100
F: +61 8 8564 3019
www.adbri.com.au

Product Certified: Type HE Brightonlite Cement
Test Certificate Number: 260071
Customer: Adbri Cement, Angaston Plant, SA
Sample Code: B0c198a
Sample Date: 04/12/2025

Nominal Blend	Requirements	Result
Clinker		>85 %
Ground Granulated Iron Blast-Furnace Slag		Nil
Mineral Addition	Max 7.5 %	<7.5 %
Calcium Sulphate		4-8 %
Minor Additional Constituents	Max 5 %	<5 %

Reportable Property	Test Method	Requirements of AS3972	Result
3 Day Strength	AS/NZS2350.11	Min 25.0 MPa	38.8 MPa
7 Day Strength	AS/NZS2350.11	Min 40.0 MPa	45.3 MPa
28 Day Strength	AS/NZS2350.11	N/R	58.5 MPa
Initial Set Time	AS/NZS2350.4	Min 45 min	75 min
Final Set Time	AS/NZS2350.4	Max 360 min	135 min
Soundness	AS/NZS2350.5	Max 5 mm	1 mm
Sulfuric Anhydride content (SO_3)	AS2350.2	Max 3.5 %	2.6 %
Chloride Ion	AS3583.13	Max 0.10 %	0.003 %
Other Properties			
SiO_2	AS2350.2	N/R	21.6 %
Al_2O_3	AS2350.2	N/R	4.9 %
Fe_2O_3	AS2350.2	N/R	0.6 %
CaO	AS2350.2	N/R	64.9 %
MgO	AS2350.2	N/R	0.9 %
Na_2O Equivalent	AS2350.2	N/R	0.3 %
Loss on Ignition	AS2350.2	N/R	3.6 %
Fineness Index	AS/NZS2350.8	N/R	465 m^2/kg
Normal Consistency	AS/NZS2350.3	N/R	29.8 %
Brightness (L)*	BH-TM-0552	N/R	72

This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adbri Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.
This despatch grab sample complies to the requirements of AS3972:2010, Type HE Cement.
* NATA Accreditation No 252 does not cover the performance of this service.
N/R = No Requirement

NATA
WORLD RECOGNISED ACCREDITATION

Accredited for compliance with ISO/IEC 17025 - Testing.

Approved Signatory
M. Wythe

Issue Date: 01/03/2026