ADBRI Cement
ABN 96 007 870 199

Quicklime Test Certificate

Final

845 Stockwell Road, Angaston SA 5353
PO Box 229, Angaston SA 5353
T: +61 8 8561 3100
F: +61 8 8564 3019
www.adbri.com.au

Product Certified: Quicklime
Test Certificate Number: 260075
Customer: Adbri Cement, Angaston Plant, SA
Sample Code: A08e508
Sample Date: 02/01/2026

Reportable Property	Test Method	Requirements of AS1672.1	Result
CHEMICAL ANALYSIS			
Available Lime (CaO)	AS4489.6.1	Min 60 %	86.6 %
Magnesium Oxide	AS4489.5.1	N/R	1.1 %
Calcium Oxide	AS4489.5.1	N/R	93.5 %
Loss On Ignition	AS4489.7.1	N/R	2.0 %
Carbon Dioxide	BH-TM-0547	Max 5 %	1.8 %
PHYSICAL TESTING			
Temperature Rise in 30 seconds	AS4489.3.1	N/R	8 ^{0}C
Total Temperature Rise	AS4489.3.1	N/R	46 ^{0}C
Total Slaking Time	AS4489.3.1	N/R	13 min
600 µm Residue on Slaking	AS4489.3.1	Max 20 %	<0.1%

This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adbri Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.
This despatch grab sample complies to the requirements of AS1672.1:1997, Quicklime.
N/R = No Requirement

NATA
WORLD RECOGNISED ACCREDITATION

Accredited for compliance with ISO/IEC 17025 - Testing.

Approved Signatory
M. Wythe

Issue Date: 01/03/2026